

REXtac Product Listing

1000 Series >>>> Laminates

PRODUCT	POLYMER TYPE	BROOKFIELD VISCOSITY cps (@ 190 °C)	NEEDLE PEN {dmm}	R & B SOFT POINT		GLASS TRANSITION		OPEN TIME sec	TENSILE STRENGTH	
				°C	°F	°C	°F		Mpa	psi
1115	Homopolymer	1500	12	155	310	■	■	0	■	■
1215	Low Ethylene Copolymers	1500	20	145	295	■	■	10	■	■
1230	Low Ethylene Copolymers	3000	14	145	295	■	■	10	■	■
1310	Medium Ethylene Copolymers	1000	25	138	280	■	■	20	■	■
1315	Medium Ethylene Copolymers	1500	28	141	285	-29	-20	20	0.57	83
1320	Medium Ethylene Copolymers	2000	25	138	280	■	■	20	■	■
1330	Medium Ethylene Copolymers	3000	23	141	285	■	■	20	■	■

2000 Series >>>> Adhesives

2104	Homopolymer	400	10	155	310	■	■	■	■	■
2115	Homopolymer	1500	10	152	305	-20	-4	■	■	■
2180	Homopolymer	8000	10	157	315	-20	-4	<5	3.31	480
2215	Low Ethylene Copolymers	1500	16	143	290	-22	-8	10	0.87	126
2280	Low Ethylene Copolymers	8000	15	146	295	-22	-8	10	1.09	158
2304	Medium Ethylene Copolymers	450	30	141	285	-29	-20	20	0.55	80
2315	Medium Ethylene Copolymers	1500	28	141	285	-29	-20	20	0.57	83
2330	Medium Ethylene Copolymers	3000	20	141	285	-29	-20	20	0.82	120
2385	Medium Ethylene Copolymers	8500	20	141	285	-29	-20	20	0.80	116
2535	High Ethylene Copolymers	3500	45	132	270	-37	-35	60	0.34	50
2585	High Ethylene Copolymers	8500	40	132	270	-37	-35	60	0.34	50
2715	Butene-1 Copolymers	1500	35	110	230	-23	-9	120	0.38	55
2721	Butene-1 Copolymers	2100	29	110	230	-23	-9	120	0.38	55
2723	Butene-1 Copolymers	2300	30	110	230	-23	-9	300	0.31	45
2730	Butene-1 Copolymers	3000	30	110	230	-23	-9	300	0.31	45
2732	Butene-1 Copolymers	3000	22	121	250	-22	-8	120	0.59	85
2780	Butene-1 Copolymers	8000	25	110	230	-23	-9	300	0.48	70

PRODUCT	POLYMER TYPE	BROOKFIELD VISCOSITY cps (@ 190 °C)	NEEDLE PEN {dmm}	R & B SOFT POINT		GLASS TRANSITION		OPEN TIME sec	TENSILE STRENGTH	
				°C	°F	°C	°F		Mpa	psi
2830	Butene-1 Copolymers	3000	10	90	200	-23	-9	450	2.42	350
2880	Butene-1 Copolymers	8000	8	93	210	-35	-37	450	3.00	430
E45	Butene-1 Copolymers	14000	30	110	230	-23	-9	900	■	■
E101	Modified t-APAO	2000	35	105	220	■	■	900	0.20	29
E200	Modified t-APAO	2000	35	105	220	■	■	900	■	■
9720	Modified t-APAO	2000	28	116	240	■	■	400	0.37	54

3000 Series >>>> Modified Bitmen Roofing

3115	Homopolymer	1500	12	155	315	■	■	■	■	■
3180	Homopolymer	8000	10	157	318	■	■	<5	3.31	480
3215	Low Ethylene Copolymers	1500	18	143	290	■	■	■	■	■
3280	Low Ethylene Copolymers	8000	15	146	295	-22	-8	■	■	■
3315	Medium Ethylene Copolymers	1500	28	141	285	-29	-20	20	0.57	83
3330	Medium Ethylene Copolymers	3000	20	141	285	-26	-15	■	■	■
3350	Medium Ethylene Copolymers	5000	20	141	285	-26	-15	■	■	■
3360	Medium Ethylene Copolymers	6000	20	141	285	-26	-15	■	■	■
3385	Medium Ethylene Copolymers	8500	20	141	285	-26	-15	■	■	■
3445	High Ethylene Copolymers	4500	31	141	285	-26	-15	■	■	■
3460	High Ethylene Copolymers	6000	30	138	280	-27	-17	30	■	■
3485	High Ethylene Copolymers	8500	25	141	285	-26	-15	■	■	■
34105	High Ethylene Copolymers	10500	25	141	285	-26	-15	■	■	■
3535	High Ethylene Copolymers	3500	45	132	270	-37	-35	60	0.34	50
3585	High Ethylene Copolymers	8500	50	132	270	-37	-35	60	0.35	50

4000 Series >>>> Wire & Cable

4304	Medium Ethylene Copolymers	450	30	141	285	-29	-20	20	0.55	80
4330	Medium Ethylene Copolymers	3000	20	141	285	-29	-20	20	0.82	119
4535	High Ethylene Copolymers	3500	45	132	270	-37	-35	60	0.34	50
4730	Butene-1 Copolymers	3000	30	110	230	-23	-9	300	0.31	45
4780	Butene-1 Copolymers	8000	25	110	230	-23	-9	300	0.48	70